

## Properties

### A5734

Glass fiber-reinforced flame retardant PA/ABS resin (GF20%, UL94 V-0)

Properties	Test methods	Test conditions	Units	Dry	1.0% moist.
Mold shrinkage	ASTM D955	-	%	0.2-0.5	-
Tensile strength	ISO 527	-	MPa	106	86
Flexural strength	ISO 178	-	MPa	171	136
Flexural modulus	ISO 178	-	MPa	6400	4800
Notched Charpy impact strength	ISO 179/1eA	23 deg C	kJ/m <sup>2</sup>	11	12
Notched Izod impact strength	ASTM D256	23 deg C/6.4mm	J/m	110	-
Rockwell hardness	ISO 2039	-	-	R116	R115
Deflection temperature under load	ISO 75	1.80MPa	deg C	194	190
Deflection temperature under load	ASTM D648	1.82MPa/6.4mm	deg C	198	-
Deflection temperature under load	ISO 75	0.45MPa	deg C	216	214
Deflection temperature under load	ASTM D648	0.46MPa/6.4mm	deg C	217	-
Coefficient of linear thermal expansion	ISO 11359	MD	X1E-5/deg C	5	-
Coefficient of linear thermal expansion	ISO 11359	TD	X1E-5/deg C	10	-
Flammability	UL94	-	-	V-0/1.5mm	-
Water absorption	ISO 62	-	%	0.6	-
Density	ISO 1183	-	g/cm <sup>3</sup>	1.46	-

Note

- Values are typical, not quality assured.
- UL recognition File No. of Daicel Polymer is E47773.

### Typical settings for processing

Preliminary drying	Barrel temperature(deg C)				Screw rotation (rpm)	Back pressure (MPa)	Mold temperature (deg C)
	Nozzle	Front	Middle	Back			
4-5hrs 90-100deg C	230-250	240-260	230-250	180-210	50-80	10-20	70-90